

# EF51 EPDM

16/07/2014



## EPDM SHEETING: STANDARD LEVEL QUALITY

### FEATURES

Standard EPDM.

### ADVANTAGES

- Very good resistance to ozone
- Good ageing resistance
- Good temperature resistance
- Good ratio quality/price

### BENEFITS


- Service life
- Economy

### APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general purpose applications in contact with water, oxidizing and non oxidizing diluted acids.

[www.trelleborg.com/elastomerlaminates](http://www.trelleborg.com/elastomerlaminates)

## MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

Measured characteristics		Standard	Value	
<b>MECHANICAL</b>				
<i>Rubber compound - black</i>			EPDM 	
<i>Density</i>			1.30 ± 0.05	g/cm <sup>3</sup>
<i>Hardness</i>		ASTM D2240	65 ± 5	Shore A
<i>Tensile strength</i>		ISO 37	≥ 5	MPa
<i>Elongation at break</i>		ISO 37	≥ 200	%
<i>Tear resistance</i>		ISO 34-1	≥ 20	N/mm
<i>Compression set after 22 h at 70 °C</i>		ISO 815-1	≤ 40	%
<i>Compression set after 22 h at 100 °C</i>		ISO 815-1	≤ 60	%
<b>TEMPERATURE</b>				
<i>Working temperature</i>			- 25/+ 120	°C
<b>AGEING</b>				
<i>Δ Tensile strenght after 70 h at 70 °C</i>		ASTM D573	≤ - 30	%
<i>Δ Elongation at break after 70 h at 70 °C</i>		ASTM D573	≤ - 50	%
<i>Ozone resistance, 200 pphm, 48 h, 40 °C, 20 %</i>		ISO 1431-1 method A	No crack	
<b>CHEMICAL RESISTANCE</b>				
<i>Diluted acids and bases</i>	<i>Concentrated acids and bases</i>	<i>Ozone</i>	<i>Oils and hydrocarbons</i>	
<b>Very good</b>	<b>Medium</b>	<b>Very good</b>	<b>Non suitable</b>	

## DIMENSIONS

Thickness (mm)	Width (mm)	Length (m)	Weight (kg/m <sup>2</sup> )	Sides finish	
1	± 0.3	1400 ± 2 %	20 ± 2 %	1.30	2 smooth sides
1.5	± 0.3	1400 ± 2 %	15 ± 2 %	1.95	2 smooth sides
2	± 0.3	1400 ± 2 %	15 ± 2 %	2.60	2 smooth sides
3	± 0.3	1400 ± 2 %	10 ± 2 %	3.90	2 smooth sides
4	± 0.4	1400 ± 2 %	10 ± 2 %	5.20	2 smooth sides
5	± 0.4	1400 ± 2 %	10 ± 2 %	6.50	2 smooth sides
6	± 0.5	1400 ± 2 %	10 ± 2 %	7.80	2 smooth sides
8	± 0.7	1400 ± 2 %	5 ± 2 %	10.40	2 smooth sides
10	± 1.0	1400 ± 2 %	5 ± 2 %	13.00	2 smooth sides
12	± 1.0	1400 ± 2 %	5 ± 2 %	15.60	2 smooth sides
15	± 1.0	1400 ± 2 %	5 ± 2 %	19.50	2 smooth sides
20	± 1.4	1400 ± 2 %	5 ± 2 %	26.00	2 smooth sides

## IDENTIFICATION

<i>Branding</i>	Without.
<i>Packaging</i>	Thickness ≤ 6 mm rolled on cardboard tube Ø 80 mm. Thickness > 6 mm in roll.
<i>Wrapping</i>	Black polyethylene film.
<i>Labelling</i>	Self-adhesive label indicating product name, dimensions, area in m <sup>2</sup> , nominal weight, and product code to allow product traceability.